#### PRODUCT NAME

# **Cem-Kote<sup>TM</sup> CW Plus**



**ANSI/NSF Standard 61** 

**Drinking Water System** Components



# **Capillary/Crystalline Waterproofing**

## MANUFACTURER

# Gemite<sup>®</sup> Products Inc.

**Toll Free:** 888-4-GEMITE (888-443-6483) E-mail: techinfo@gemite.com Web Site: www.gemite.com

USA 160-3480 East Robinson Rd. Amherst, New York 14228 Phone 888-443-6483 Fax 888•443•6329

# CANADA

1787 Drew Road Mississauga, Ontario L5S 1J5 905-672-2020 Phone Fax 905•672•6780

#### **FEATURES**

- **Approved ANSI/NSF Standard 61- Barrier Materials**
- Negative or positive side waterproofing
- Permanently active (in-depth)
- Seals cracks up to 0.5 mm •
- Fast cure waterproofing (48 hours)
- Approved for potable water tanks >10,000 USG (38 m3)
- Waterproofs highly porous concrete
- Non-flammable •
- One component (add water only)
- More economical than competitive products
- Inorganic & Environment friendly
- Long working time 30 minutes plus

#### **PRODUCT DESCRIPTION**

#### **Basic Use**

Cem-Kote CW Plus is a crystalline (capillary) in-depth water- TECHNICAL DATA proofing for new or existing water & wastewater storage tanks, digesters, clarifiers & utility vaults. Cem-Kote CW Plus is used to waterproof retaining walls, basements, floor slabs, swimming pools and other concrete structures.

#### **Composition and Materials**

Cem-Kote CW Plus is 1-component (add water only), Portland cement based coating (slurry), containing silica based materials. Under water pressure (negative or positive), the soluble silicate penetrates (due to osmotic pressure) into the substrate, where it reacts with lime and forms insoluble calcium silicate crystals which "plug" the capillary pores and waterproof the concrete while allowing the water vapor to pass.



#### Limitations

Cem-Kote CW Plus is a fast setting material. Under normal conditions it should be applied within 15-30 minutes after mixing. Mix only the amount of material which can be applied within this period of time. Do not apply Cem-Kote CW Plus when the temperature is expected to be below  $4^{\circ}C (40^{\circ} \text{ F})$ , or when rain is imminent.

#### Health and Safety

Cem-Kote CW Plus is non-toxic and non-flammable. Your skin might be sensitive to cement. We recommend use of rubber gloves. Avoid contact with skin. If contact occurs, flush immediately with water. Seek medical advice if irritation occurs. Harmful if digested. Keep product out reach of children. FOR INDUSTRIAL USE ONLY. Consult MSDS for additional information.

### Color

Industrial Grey

#### Packaging

Cem-Kote CW Plus Premix is a one component material packaged in 22.7 kg (50 lbs) bags.

#### Yield

*Cem-Kote CW Plus Premix* yields 13.2 L (0.47 ft<sup>3</sup>) and the theoretical coverage is 22.7 m<sup>2</sup>  $\overset{\circ}{=}$  the rate of 1 kg/m<sup>2</sup> (244 ft<sup>2</sup>  $\overset{\circ}{=}$  the rate of  $1.84 \text{ lbs/ yd}^2$ ). The rate of application varies depending upon the actual end use, as specified.

The actual coverage will depend on surface roughness and the thickness applied. The applicator must carry out a sample application to determine the actual coverage for the given substrate and application rate.

#### **Storage and Transportation**

Cem-Kote CW Plus stored on pallets in a dry, cool area has a shelf-life of 12 months. Packaged 55 bags per pallet.

Compressive Strength (ASTM C109 Modified)	56.9 - 62.3 MPa (8,250 - 9033 psi)
Modulus of Rupture (ASTM C348) 28 days	6.2 - 8.3 MPa (900 - 1,200 psi)
Bond Strength with Con- crete (Pull off test)	Greater than the tensile strength of the concrete substrate
Water Vapor Permeance 3 mm (1/8 in) thickness	1.8 metric perms
Hydraulic Permeability	Concrete block coated with <i>Cem-Kote CW Plus</i> withstands 156 m (500 ft) water head pressure

Cem-Kote CW Plus - page 1 of 2

Gemite Products Inc.

#### **INSTALLATION**

#### Current Guide Specification & Application Instructions contain Moist cure Cem-Kote CW Plus for 3 days. Protect the surface additional information specific to each application and must be from rapid drying. When working under tarps at freezing temfollowed. Contact Gemite's Technical Service for information specific to your application.

#### **Surface Preparation**

Remove all loose and deteriorated concrete, laitance, dust, dirt and efflorescence. Use high-pressure waterblast min. 6,000 psi (41 Mpa), or sandblasting. Correct surface preparation is essential for successful application of Cem-Kote CW Plus.

The active water leaks must be stopped using Fibre-Patch WP (water plug) and deeper surface deterioration repaired with *Fibre-Patch OV*. Leave the surface of *Fibre-Patch OV* rough & clean thoroughly with high pressure water before application of None required. Cem-Kote CW Plus.

Cem-Kote CW Plus should be applied within 48 hours after the surface repair.

#### **Reinforcing Steel**

Remove all loose rust from any exposed reinforcing steel and apply two coats of Fibre-Prime rustproofing.

#### **Crack Treatment**

Any existing cracks must be treated separately using Cem-Kote Flex ST or Cem-Kote Flex Plus.

#### Mixing

Mix each 22.7 kg (50 lbs) bag with approx. 4.3-4.5 L (1.1-1.2 USG) of water, depending on required consistency. Use a drill (400-600 rpm) with a mixing paddle. Gradually add the dry material into water and mix until a smooth and lump free mix is obtained. Adjust the water to obtain a brushable consistency, or stiffer consistency for trowel application. Do not over mix.

#### Application

Brush apply Cem-Kote CW Plus in 2 (two) consecutive coats to achieve the specified application rate 0.75-1.5 kg/m<sup>2</sup> (1.4-2.8  $lbs/yd^2$ ). No wetting is required between coats. The re-coating must be done within  $\frac{1}{2}$  to 1 hour.

When layers over 3 mm (1/8 in) are required, apply a thin layer of Cem-Kote CW Plus as a bonding agent using brush or broom.

Apply second, stiffer consistency, coat of Cem-Kote CW Plus into the wet slurry by trowel. Keep wet edge. Do not build up a layer thicker than 6 mm (1/4 in). In new construction, Cem-Kote *CW Plus* is dry-sprinkle applied onto the surface of the freshly poured slabs (after the concrete starts to reach initial set) and is power trowel finished.

Follow the current Gemite's Guide Specifications, Application Instructions and the specified rate of application.

#### Curing

peratures, avoid using propane heaters. Use only electrical heaters to prevent "carbonation" of Cem-Kote CW Plus.

### **Clean** Up

All tools and equipment must be cleaned with water immediately after use. Cured material must be removed mechanically.

#### AVAILABILITY AND COST

Cem-Kote CW Plus is available worldwide. Contact Gemite for the nearest Representative or Distributor and current pricing.

#### MAINTENANCE

#### WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For details, contact Gemite's head office.

#### **TECHNICAL SERVICE**

For advice on suitability of Cem-Kote CW Plus for specific application, specification assistance and application instructions, contact Technical Service: USA 888-443-6483 or Canada 905-672-2020.

#### **Short Specification**

The reactive capillary/crystalline waterproofing shall be Cem-Kote CW Plus, as manufactured by Gemite Products Inc., [USA 888-443-6483] [Canada 905-672-2020]. It will meet all the Technical Data specified in the current Cem-Kote CW Plus Product Data Sheet.